

Amendments to the Claims:

This listing of claims will replace all prior versions and listings of claims in this application:

Listing of Claims:

1. (Currently Amended)

A process for manufacturing a fibrin membrane, characterized in that it comprises the steps of:

- a) adding a physiological coagulating agent to blood plasma, up to gelling and clot formation;
- b) removing ~~the a~~ transudate from said blood clot by means of ~~physiologic a~~ physiological absorbent agents agent to form a membrane;
- c) washing said ~~blood clot~~ membrane with ~~a~~ dehydrating and ~~a~~ softening ~~agents~~ agent; and
- d) drying and sterilizing said ~~dehydrated blood clot~~ washed membrane.

2. (Currently Amended)

The process according to claim 1, characterized in that said physiological ~~clotting~~ coagulating agent is calcium chloride.

3. (Currently Amended)

The process according to claim 1 or 2, characterized in that said physiological absorbent ~~agents are~~ agent is an inorganic ~~salts~~ salt.

4. (Currently Amended)

The process according to claim 3, characterized in that said inorganic ~~salts are~~ salt is NaCl, NaHCO₃, or a mixture thereof.

5. (Currently Amended)

The process according to ~~one of the previous claims~~ claim 1, characterized in that said

softening agents are low-boiling alcohols agent is an alcohol in propane-triol, in particular ethanol in propane-triol.

7/6. (Withdrawn)

A fibrin membrane, characterized in that it is obtained by ^{The} ^{claim 1} a process according to ~~one or~~ more previous claims.

8/7. (Withdrawn)

The fibrin membrane according to claim ⁷ ~~6~~, characterized in that it shows a modulus of elasticity between 0.070 and 2.600 N/mm.

9/8. (Withdrawn)

The fibrin membrane according to claim ~~6~~ or ⁷ ~~7~~, characterized in that it shows a breaking limit between 0.030 and 0.350 N/mm.

10/8. (Withdrawn)

The fibrin membrane according to ^{claim 7} ~~one or more claims from 6 to 8~~, characterized in that it shows a proportionality limit tension/strain between 0.025 and 0.085 N/mm.

11/10. (Withdrawn)

The fibrin membrane according to ^{claim 7} ~~one or more claims from 6 to 9~~, characterized in that it is ^{impregnated} ~~soaked~~ with disinfectant agents.

12/11. (Withdrawn)

The fibrin membrane according to ^{claim 7} ~~one or more claims from 6 to 10~~, characterized in that it is ^{impregnated} ~~soaked~~ with drugs.

13/12. (Withdrawn)

The fibrin membrane according to ^{claim 7} ~~one or more claims from 6 to 11~~, characterized in that it is ^{impregnated} ~~soaked~~ with tissue growth factors.

6/8 (New)

The process according to claim 5, characterized in that said alcohol in propane-triol is ethanol in propane-triol.